

CERAMIC PRO PPF & VINYL TOP COAT

PRODUCT IDENTIFICATION

PRODUCT NAME	Ceramic Pro PPF & Vinyl Top Coat
PRODUCT VERSION	V1.0
PRODUCT CODE	NS100-P
DOCUMENT REVISION	V1.0-R3
ISSUE DATE	2026-09-01
MANUFACTURER	Nanoshine Group Corp.
COUNTRY OF MANUFACTURE	Taiwan (R.O.C.)



PRODUCT DESCRIPTION

TECHNICAL DESCRIPTION	Ceramic Pro PPF & Vinyl Top Coat is a nano-ceramic finishing coating developed for compatible paint protection films and vinyl surfaces as the final layer of the Ceramic Pro PPF & Vinyl coating system. It provides strong hydrophobic performance, reduced contaminant adhesion, improved surface slickness, and easier maintenance while enhancing the visual appearance of the treated film. The coating also adds an additional protective barrier against environmental exposure and everyday surface contamination.
PRODUCT CLASS	Hydrophobic Surface Treatment
FORMULATION SYSTEM	Solvent-Based
SOLVENT / CARRIER TYPE	Hydrocarbon-Based
COMPONENT CONFIGURATION	Single-Component (1K)
TECHNOLOGY	Nano-Ceramic Coating Technology
SYSTEM ROLE	Top Coat / Finishing Coat
LAYERING TYPE	Single-Layer Coating

CURING MODE	Ambient Cure
COATING PERMANENCE	Semi-Permanent (1 year)
PRIMARY FUNCTIONS	Stain Resistance / Hydrophobic Performance / Water Repellency / Contaminant Repellency / Self-Cleaning Performance / Reduced Surface Adhesion / Easier Maintenance / Surface Slickness / Gloss Enhancement / Visual Depth Enhancement / Color Enhancement

TYPICAL TECHNICAL PROPERTIES

PROPERTY	VALUE	TEST METHOD / STANDARD
AS SUPPLIED		
Density	0.9-0.95 g/cm³ at 25 °C	ASTM D1475
Viscosity	<5 mPa·s at 20 °C	ASTM D2196
CURED COATING		
Water Contact Angle	120°	ASTM D7334

APPEARANCE

LIQUID APPEARANCE	Clear, colorless, homogeneous liquid, free from visible particles or sediment
CURED APPEARANCE	Clear and transparent; Gloss

INTENDED USE

INTENDED USE DESCRIPTION	Ceramic Pro PPF & Vinyl Top Coat is primarily intended as the finishing layer of the Ceramic Pro PPF & Vinyl coating system, applied after the Base Coat to complete the system and enhance its hydrophobic performance. It is mainly used on automotive PPF and vinyl surfaces, as well as in other applications where compatible protective films and vinyl materials are used.
APPLICATION AREAS	Automotive / Transportation / Marine
SUITABLE SUBSTRATES	
Protective Films & Flexible Surface Materials	PPF / Vinyl / Other Surface Films
SURFACE FINISH COMPATIBILITY & RETENTION	Gloss — Preserved; Satin — Application-Dependent; Matte —

	Application-Dependent
USE ENVIRONMENT	Exterior
APPLICATION LEVEL	Professional Use Only

RESTRICTIONS AND LIMITATIONS

SUBSTRATE DEFORMATION LIMITATIONS	Not suitable for substrates subject to significant stretching or repeated elongation.
EXISTING SURFACE TREATMENT LIMITATIONS	Do not apply over existing waxes, sealants, hydrophobic treatments, or protective coatings unless specifically approved.

SURFACE REQUIREMENTS

SURFACE CLEANLINESS	Fully Clean / Free from Oils, Grease, Silicone, Waxes, Polishing Residues, Existing Coatings (unrelated to the current build), and Other Contaminants
SURFACE MOISTURE CONDITION	Fully Dry
SURFACE TEMPERATURE	Recommended range: 10–30 °C
EXISTING COATING / PAINT CONDITION	Fully Cured / Fully Dried and Ready for Service

For complete substrate preparation procedures and product-specific preparation steps, refer to the current Installation Manual.

APPLICATION CONDITIONS

APPLICATION METHOD	Applicator Application
RECOMMENDED AMBIENT TEMPERATURE	25 °C
RECOMMENDED RELATIVE HUMIDITY	50% RH
APPLICATION ENVIRONMENT	Clean, Dust-Free Indoor Area / Clean Controlled Area
RECOMMENDED LAYERS	1
CONSUMPTION PER LAYER	10-15 ml/m ² per layer

APPLICATION & CURING REFERENCE CONDITIONS

The application and curing times stated in this document are provided as reference values based on an ambient temperature of 25 °C, 50% relative humidity, and the typical coating thickness specified in this TDS. Actual timing may vary depending on substrate type and absorbency, application method, applied product quantity, final layer thickness after leveling, environmental conditions, and installer technique. The stated values should therefore be used as a technical reference rather than absolute process limits. During application, coating behavior should be observed and timing adjusted where necessary to achieve the intended result.

APPLICATION TIMING

FLASH TIME	30-60 seconds after application
LEVELING / WIPE-OFF WINDOW	approximately 60 seconds
MINIMUM INTERCOAT INTERVAL	40 minutes
MAXIMUM INTERCOAT INTERVAL	60 minutes

CURING

TACK-FREE TIME	1 hour
WATER CONTACT RESTRICTION	24 hours
RELEASE FOR SERVICE / DELIVERY	24 hours
TIME BEFORE WASHING	72 hours
FULL CHEMICAL CURE	72 hours

For accelerated or alternative curing procedures (if available), refer to the current Installation Manual.

STORAGE AND SHELF LIFE

STORAGE TEMPERATURE	5–25 °C
STORAGE CONDITIONS	Store in a dry place. Do not freeze, overheat, or expose to direct sunlight.
SHELF LIFE — UNOPENED	2 years in sealed packaging
AFTER OPENING	Use as soon as possible after opening.

PACKAGING

SECONDARY PACKAGING	Rigid Presentation Box
PRIMARY CONTAINER	Glass Bottle / Aluminum Bottle
AVAILABLE VOLUMES	Glass Bottle: 50 ml / Aluminum Bottle: 1 L

HEALTH AND SAFETY

GENERAL SAFETY	Chemical product. Handle and use in accordance with the current Safety Data Sheet (SDS) and product label.
SAFETY DATA SHEET	Refer to the current product Safety Data Sheet (SDS) for complete information on hazards, safe handling, personal protective equipment, first aid, storage, disposal, transport, and emergency measures.

TECHNICAL DATA BASIS

The technical data stated in this document are based on internal laboratory testing, third-party testing where applicable, and current technical knowledge of the product.

Unless otherwise specified, all stated values are typical values obtained under controlled test conditions and are provided for technical reference. They should not be interpreted as guaranteed specification limits for every individual production batch.

Actual results may vary depending on substrate type and condition, application method, applied quantity or coating thickness, environmental conditions, curing conditions, and other application-specific factors.

Where a specific test method, standard, substrate, or test condition is relevant to the interpretation of a reported value, it should be stated together with that value.

LEGAL & TECHNICAL DISCLAIMER

The information and recommendations contained in this Technical Data Sheet are based on current product knowledge and the technical data available at the time of publication.

Actual product performance may vary depending on substrate type and condition, surface preparation, application method, environmental conditions, curing conditions, subsequent maintenance, and conditions of use. The product must be applied in accordance with the specified requirements and the current Installation Manual.

Users are responsible for verifying product suitability for the intended substrate and application, particularly where materials, conditions, or uses fall outside those specifically described or validated by the manufacturer.

This Technical Data Sheet does not replace the applicable Safety Data Sheet (SDS). Refer to the current product SDS for complete information regarding hazards, safe handling, personal protective equipment, first aid, storage, disposal, and emergency measures.

For complete surface preparation, application, curing, and installation procedures, refer to the current Ceramic Pro Installation Manual applicable to the product.

Always refer to the most recent published version of this Technical Data Sheet. Product specifications, formulations, recommendations, and supporting documentation may be updated as part of ongoing product development and technical review.

This document does not modify or replace any applicable product warranty terms or other contractual conditions.